## G-PAEK™ G-COAT 501

## Polyether Ketone

Gharda Chemicals Ltd.

## Message:

Product Details: G-COAT 500 series of water based liquid dispersions are available, where thinner coating and difficult geometries must be coated, and get enhanced properties such as wear & abrasion resistance and release properties, suitable for food contact applications, color natural. G-COAT 501: These grades have been specifically formulated to provide a resilient coating with varying levels of lubricantion to give combined high wear and abrasion resistance

General Information			
Features	Good wear resistance		
	Good wear resistance		
	Compliance of Food Exposure		
Uses	Thin coating		
	Coating application		
Appearance	Black		
	Green		
	Natural color		
Processing Method	Coating		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm³	
Water Absorption (Equilibrium)	0.060	%	ASTM D570
Solids Content	50	%	
Viscosity	1.8	min	
Maximum Layer Thickness - per coat	100.0 - 120.0	μm	
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 Cycles,			
CS-10 Wheel)	8.00	mg	ASTM D1242
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	280	°C	UL 746B
Glass Transition Temperature	152	°C	ASTM D3418
Melting Temperature	372	°C	ASTM D3418
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Additional Information	Nominal Value	Unit	

Baking Temperature: 420°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

