

# POLYelast TPE R44 TV10

Polypropylene + EPDM Rubber

Polykemi AB

Message:

Mineral reinforced

General Information			
Filler / Reinforcement	Mineral,10% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	54		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	19.0	MPa	ISO 527-2
Tensile Strain (Yield)	8.0	%	ISO 527-2
Flexural Modulus (23°C)	1300	MPa	ISO 178
Flexural Stress	25.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	15	kJ/m <sup>2</sup>	
23°C	28	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179
-20°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature <sup>1</sup> (0.45 MPa, Unannealed)	88.0	°C	ISO 75-2/B
Vicat Softening Temperature	132	°C	ISO 306/A50
NOTE			
1.	120°C/hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

**Susheng Import & Export Trading Co.,Ltd.**

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

