

Hifax TYC 773P

Thermoplastic Polyolefin Elastomer
LyondellBasell Industries

Message:

Hifax TYC 773P very high melt flow, 1,350 MPa flexural modulus, UV-stabilized, mineral-filled, paintable, thermoplastic elastomeric olefin (TEO) resin has an excellent balance of properties and processability. It was designed primarily for use in thin-walled bumper fascia applications.

General Information			
Filler / Reinforcement	Mineral		
Additive	UV Stabilizer		
Features	Good Dimensional Stability		
	Good Impact Resistance		
	Good Moldability		
	Good Toughness		
	Good Weather Resistance		
	High Flow		
	High Stiffness		
	Paintable		
Uses	Automotive Bumper		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	22	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	17.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield, 23°C	7.0	%	
Break, 23°C	500	%	
Flexural Modulus (23°C)	1350	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180
-40°C	6.0	kJ/m²	
23°C	50	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	100	°C	ISO 75-2/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

