

Durethan® BKV 30 H2.0 901510

Polyamide 6

LANXESS GmbH

Message:

PA 6, 30 % glass fibers, injection molding, heat-aging stabilized

General Information				
UL YellowCard		E245249-473587	E245249-473590	
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Additive		heat stabilizer		
Features		Good heat aging resistance		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity				
--	1.36	--	g/cm ³	ASTM D792
23°C	1.36	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 294-4
Vertical flow direction: 280°C, 2.00mm ¹	0.69	--	%	ISO 294-4
Vertical flow direction: 120°C, 2 hours, 2.00mm ²	0.13	--	%	ISO 294-4
Flow direction: 280°C, 2.00mm ³	0.30	--	%	ISO 294-4
Flow direction: 120°C, 2 hours, 2.00mm ⁴	0.060	--	%	ISO 294-4
Water Absorption				ISO 62
Saturated, 23°C	7.0	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.1	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	210	100	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C ⁵	9200	5600	MPa	ASTM D638
23°C	9500	5800	MPa	ISO 527-2/1
Tensile Strength				
Fracture, 23°C	180	100	MPa	ASTM D638
Fracture, 23°C	170	100	MPa	ISO 527-2/5
Tensile Elongation (Break, 23°C)	3.0	6.0	%	ASTM D638, ISO 527-2/5

Tensile Creep Modulus				ISO 899-1
1 hr	--	5100	MPa	ISO 899-1
1000 hr	--	4100	MPa	ISO 899-1
Flexural Modulus				
23°C	8300	5000	MPa	ASTM D790
23°C ⁶	9300	5000	MPa	ISO 178/A
Flexural Strength				
23°C	280	170	MPa	ASTM D790
3.5% strain ⁷	260	140	MPa	ISO 178/A
23°C ⁸	270	160	MPa	ISO 178
Flexural Strain at Flexural Strength ⁹ (23°C)	4.0	6.0	%	
Burning Behavior ¹⁰ (> 1.00 mm)	passed	--		ISO 3795
ISO Shortname	PA 6, GHR, 14-090, GF30	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Films	Dry	Conditioned	Unit	Test Method
Film Puncture Energy				ISO 6603-2
-- ¹¹	3.00	--	J	ISO 6603-2
-- ¹²	3.00	6.00	J	ISO 6603-2
Film Puncture Force				ISO 6603-2
-- ¹³	860	--	N	ISO 6603-2
-- ¹⁴	1000	1230	N	ISO 6603-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	10	kJ/m ²	ISO 179/1eA
23°C	10	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	65	60	kJ/m ²	ISO 179/1eU
23°C	75	90	kJ/m ²	ISO 179/1eU
Notched Izod Impact				
-40°C, 3.18 mm	100	100	J/m	ASTM D256
23°C, 3.18 mm	120	150	J/m	ASTM D256
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
23°C	10	20	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	60	55	kJ/m ²	ISO 180/1U
23°C	65	80	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				

0.45 MPa, not annealed, 3.99mm	215	--	°C	ASTM D648
0.45 MPa, not annealed	215	--	°C	ISO 75-2/B
1.8 MPa, not annealed, 3.99mm	200	--	°C	ASTM D648
1.8 MPa, not annealed	200	--	°C	ISO 75-2/A
Vicat Softening Temperature				
--	200	--	°C	ISO 306/B50
--	> 200	--	°C	ISO 306/B120
Melting Temperature ¹⁵	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	2.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.0E-4	--	cm/cm/°C	ISO 11359-2
RTI Elec				UL 746
0.830 mm	120	--	°C	UL 746
1.50 mm	120	--	°C	UL 746
RTI Imp				UL 746
0.830 mm	90.0	--	°C	UL 746
1.50 mm	95.0	--	°C	UL 746
RTI				UL 746
0.830 mm	130	--	°C	UL 746
1.50 mm	130	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+12 - 1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Dielectric Strength				IEC 60243-1
23°C, 1.00 mm	35	30	kV/mm	IEC 60243-1
23°C, 3.00 mm	40	35	kV/mm	IEC 60243-1
Dielectric Constant				IEC 60250
23°C, 50 Hz ¹⁶	4.00	15.0		IEC 60250
23°C, 1 MHz ¹⁷	4.00	5.00		IEC 60250
23°C, 100 Hz	4.20	12.0		IEC 60250
23°C, 1 MHz	3.80	4.40		IEC 60250
Dissipation Factor				IEC 60250
23°C, 50 Hz	5.0E-3	0.50		IEC 60250
23°C, 100 Hz	0.010	0.26		IEC 60250
	0.017	0.078		
23°C, 1 MHz	0.015	0.16		IEC 60250
Arc Resistance	--	76.0	sec	ASTM D495
Comparative Tracking Index				

Solution a	425	--	V	IEC 60112
--	--	400	V	ASTM D3638
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.830 mm	HB	--		UL 94
1.50 mm	HB	--		UL 94
1.60 mm	HB	--		UL 94
3.00 mm	HB	--		UL 94
3.20 mm	HB	--		UL 94
Glow Wire Flammability Index (1.50 mm)	700	--	°C	IEC 60695-2-12
Oxygen Index ¹⁸	22	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	270 - 290		°C	
Mold Temperature	80.0 - 120		°C	
NOTE				
1.	60x60x2; MT 80°C; 600 Bar			
2.	60x60x2			
3.	60x60x2; MT 80°C; 600 Bar			
4.	60x60x2			
5.	1.0 mm/min			
6.	2.0 mm/min			
7.	2.0 mm/min			
8.	2.0 mm/min			
9.	Pull Rate: 2 mm/min; 50% RH			
10.	US-FMVSS302			
11.	-30°C			
12.	23°C			
13.	-30°C			
14.	23°C			
15.	10°C/min			
16.	Tinfoil Electrodes			
17.	Tinfoil Electrodes			
18.	Procedure A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

