

LNP™ LUBRILOY™ RX05498 compound

Polyamide 66
SABIC Innovative Plastics

Message:

LNP LUBRILOY* RX05498 is a compound based on Nylon 66 resin containing Proprietary Lubricant. Added features of this material include: High Impact.
Also known as: LNP* LUBRILOY* Compound RW-HI
Product reorder name: RX05498

General Information			
Additive	Lubricant		
Features	Impact resistance, high		
	Lubrication		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	2.4 - 2.6	%	ASTM D955
Transverse flow: 24 hours	2.4 - 2.6	%	ASTM D955
Vertical flow direction: 24 hours	2.4 - 2.6	%	ISO 294-4
Flow direction: 24 hours	2.4 - 2.6	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.70	%	ASTM D570
Equilibrium, 23°C, 50% RH	1.1	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2220	MPa	ASTM D638
--	2160	MPa	ISO 527-2/1
Tensile Strength			
Yield	60.0	MPa	ASTM D638
Yield	55.0	MPa	ISO 527-2
Fracture	53.1	MPa	ASTM D638
Fracture	54.5	MPa	ISO 527-2
Tensile Elongation			
Yield	8.0	%	ASTM D638
Yield	16	%	ISO 527-2
Fracture	31	%	ASTM D638
Fracture	64	%	ISO 527-2
Flexural Modulus			
--	2080	MPa	ASTM D790
--	2000	MPa	ISO 178

Flexural Strength			
--	80.7	MPa	ASTM D790
--	74.6	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
With self-dynamics	0.31		ASTM D3702 Modified
With Self-Static	0.18		ASTM D3702 Modified
Wear Factor - Washer	8.00	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	430	J/m	ASTM D256
23°C ²	19	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	140	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	76.0	J	ASTM D3763
--	65.6	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	207	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ⁴	189	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	63.9	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁵	67.0	°C	ISO 75-2/Af
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	1.2E-4	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	1.1E-4	cm/cm/°C	ASTM E831, ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 - 0.25	%	
Rear Temperature	266 - 277	°C	
Middle Temperature	282 - 293	°C	
Front Temperature	293 - 304	°C	
Processing (Melt) Temp	282 - 304	°C	
Mold Temperature	93.3 - 110	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

