

Prime Polypro™ J715M

Polypropylene Copolymer

Prime Polymer Co., Ltd.

Message:

Prime Polypro™ J715M is a Polypropylene Copolymer (PP Copolymer) product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America.

Characteristics include:

Copolymer

Impact Resistant

General Information			
UL YellowCard	E167245-312440		
Features	Block Copolymer		
	High Impact Resistance		
Agency Ratings	JHOSPA Unspecified Rating [A]PZar-2911-L		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	90		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1300	MPa	ISO 527-2
Tensile Stress (Yield)	27.0	MPa	ISO 527-2
Tensile Strain (Break)	100	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			ISO 179
-20°C	4.0	kJ/m²	
23°C	9.0	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

