

HiFill® PC/PBT IM 5220 UV BK

Polycarbonate + PBT
Techmer Engineered Solutions

Message:

HiFill® PC/PBT IM 5220 UV BK is a Polycarbonate + PBT (PC+PBT) product. It can be processed by injection molding and is available in North America. Characteristics include:
Flame Rated
Good UV Resistance
Impact Modified
UV Stabilized

General Information			
Additive	Impact Modifier		
	UV Stabilizer		
Features	Good UV Resistance		
	Impact Modified		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.70	%	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	52.4	MPa	ASTM D638
Tensile Elongation (Yield)	130	%	ASTM D638
Flexural Modulus	2000	MPa	ASTM D790
Flexural Strength	84.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	107	°C	
1.8 MPa, Unannealed	98.9	°C	
CLTE - Flow	2.3E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.57 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	98.9	°C	

Drying Time	4.0	hr
Rear Temperature	238 to 266	°C
Middle Temperature	238 to 266	°C
Front Temperature	238 to 266	°C
Processing (Melt) Temp	238 to 266	°C
Mold Temperature	54.4 to 93.3	°C
Back Pressure	0.172 to 0.414	MPa
Screw Speed	30 to 60	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

