

Vyncolit® RX®1-501N

Diallyl Phthalate

Vyncolit N.V.

Message:

1-501N is a mineral filled diallyl ortho-phthalate molding compound, which meets the requirements of ASTM D5948 Type MDG.

General Information	
Filler / Reinforcement	Mineral filler
Features	Good dimensional stability
	Moisture resistance
	Antibacterial property
	Solvent resistance
	Impact resistance, high
	Good electrical performance
	Good chemical resistance
	alkali resistance
	Good wear resistance
	Fuel resistance
	Heat resistance, high
	acid resistance
	Flame retardancy
Uses	Membrane key switch
	Aircraft applications
	Insulating material
	Connector
	Communication Equipment
Agency Ratings	ASTM D 5948, Type MDG
	MIL C-24308
Appearance	Brown
	Black
	Red
	Blue
	Green
Forms	Particles
Processing Method	Resin transfer molding
	Compression molding

Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80	g/cm ³	ASTM D792
Molding Shrinkage - Flow (Compression Molded)	0.30 - 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, Compression Molded)	55.2	MPa	ASTM D638
Flexural Modulus (Compression Molded)	11700	MPa	ASTM D790
Flexural Strength (Break)	110	MPa	ASTM D790
Compressive Strength	145	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression Molded)	24	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, Compression Molded)	166	°C	ASTM D648
Linear thermal expansion coefficient			ASTM E831
Flow	2.5E-5	cm/cm/°C	ASTM E831
Lateral	2.5E-5	cm/cm/°C	ASTM E831
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹	16	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
1 kHz	4.20		ASTM D150
1 MHz	3.60		ASTM D150
Dissipation Factor			ASTM D150
1 kHz	0.013		ASTM D150
1 MHz	0.014		ASTM D150
Arc Resistance	140	sec	ASTM D495
Comparative Tracking Index (CTI)	600	V	UL 746
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.59 mm	HB		UL 94
3.18 mm	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	60.0	°C	
Middle Temperature	76.7	°C	
Nozzle Temperature	87.8	°C	

Processing (Melt) Temp	110 - 116	°C
Mold Temperature	160 - 182	°C
Injection instructions		
Plastication: 50rpmBack Pressure (gauge): slightInjection Pressure: set to give 5 to 15 sec injection timeHold Pressure: 1/2 of injection pressureCure Time, 0.125 in: 40 secWater Absorption, ASTM D570, 48 hrs, 50°C: 0.3%Dielectric Strength, ASTM D149, 60 Hz, Method B, wet: 15.8 kV/mmDielectric Constant, ASTM D150, 1000 Hz, wet: 4.2Dielectric Constant, ASTM D150, 1000000 Hz, wet: 3.6Dissipation Factor, ASTM D150, 1000 Hz, wet: 0.013Dissipation Factor, ASTM D150, 1000000 Hz, wet: 0.014Compression and Transfer Molding Conditions: Preforming Pressure: 8000 to 12000 psi Preheat Temperature: 220 to 230 °F Preheat Time: 45 sec Mold Temperature: 320 to 350 °F Compression Mold Pressure: 3500 to 6000 psi Transfer Mold Pressure: 2500 to 5000 psi Cure Time, 0.125 in: 45 to 70 sec		
NOTE		

- Method B (step by step)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT