Teldene® H08ML

Polypropylene Homopolymer

National Petrochemical Industries Company (NATPET)

Message:

Typical Applications

Used for the production of consumer goods such as food containers, house wares, toys and garden furniture

Components for appliances and parts for the automotive industry

Key Characteristics

Good flow properties, High stiffness, easy processing

Food contact approval for specific applications (refer to NATPET)

General Information				
Features	Rigidity, high			
	Homopolymer			
	Workability, good			
	Good liquidity			
	Compliance of Food Exposure			
Uses	Home appliance components			
	Furniture			
	Household goods			
	Application in Automobile Field			
	Food container			
	Toys			
Processing Method	Extrusion			
	Injection molding			
District.	No	11.50	To d Malle of	
Physical	Nominal Value	Unit	Test Method	
		3		
Density (23°C)	0.900	g/cm³	ISO 1183	
·	9.0	g/cm³ g/10 min	ISO 1183 ASTM D1238	
Melt Mass-Flow Rate (MFR) (230°C/2.16				
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ASTM D1238	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) Mechanical	9.0	g/10 min	ASTM D1238 Test Method	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) Mechanical Tensile Stress	9.0 Nominal Value	g/10 min Unit	ASTM D1238 Test Method ISO 527-2/50	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) Mechanical Tensile Stress Yield	9.0 Nominal Value	g/10 min Unit MPa	ASTM D1238 Test Method ISO 527-2/50 ISO 527-2/50	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) Mechanical Tensile Stress Yield Fracture	9.0 Nominal Value	g/10 min Unit MPa	ASTM D1238 Test Method ISO 527-2/50 ISO 527-2/50 ISO 527-2/50	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) Mechanical Tensile Stress Yield Fracture Tensile Strain	9.0 Nominal Value 34.0 24.0	g/10 min Unit MPa MPa	ASTM D1238 Test Method ISO 527-2/50 ISO 527-2/50 ISO 527-2/50 ISO 527-2/50	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) Mechanical Tensile Stress Yield Fracture Tensile Strain Yield	9.0 Nominal Value 34.0 24.0	g/10 min Unit MPa MPa MPa	ASTM D1238 Test Method ISO 527-2/50 ISO 527-2/50 ISO 527-2/50 ISO 527-2/50 ISO 527-2/50	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) Mechanical Tensile Stress Yield Fracture Tensile Strain Yield Fracture	9.0 Nominal Value 34.0 24.0 13 > 50	g/10 min Unit MPa MPa MPa % %	ASTM D1238 Test Method ISO 527-2/50 ISO 527-2/50 ISO 527-2/50 ISO 527-2/50 ISO 527-2/50 ISO 527-2/50	

Thermal	Nominal Value	Unit	Test Method	
Heat Deflection Temperature (0.45 MPa,				
Unannealed)	115	°C	ISO 75-2/B	
Vicat Softening Temperature	155	°C	ISO 306/A50	
Extrusion	Nominal Value	Unit		
Melt Temperature	240 - 260	°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

