

Hyundai EP PA6 LS165

Polyamide 6
HYUNDAI EP Co., Ltd.

Message:
Hyundai EP PA6 LS165 is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It is available in Asia Pacific. Typical application: Electrical/Electronic Applications. Primary characteristic: heat stabilizer.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	General Purpose		
	Heat Stabilized		
Uses	Electrical/Electronic Applications		
	General Purpose		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.38	g/cm ³	ASTM D1505
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Ash Content	30	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	177	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	8340	MPa	ASTM D790
Flexural Strength	240	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	210	°C	ASTM D648
Melting Temperature	220	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13 to 1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	3.8	kV/mm	ASTM D149

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

