

# DEXFLEX® 911-UV

Polypropylene

LyondellBasell Industries

## Message:

Dexflex 911-UV is a 10% talc filled, UV stabilized, high impact thermoplastic olefinic elastomer

General Information		
Filler / Reinforcement	Talc filler, 10% filler by weight	
Additive	UV stabilizer	
Features	Impact resistance, high	
Uses	Application in Automobile Field Automotive exterior parts	
Processing Method	Injection molding	
Physical	Nominal Value	Unit
Density	0.960	g/cm <sup>3</sup>
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	22	g/10 min
Mechanical	Nominal Value	Unit
Tensile Strength (Yield)	21.5	MPa
Flexural Modulus	1450	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

