

# ALTECH® PP-H A 2030/156 GF30 CP

Polypropylene Homopolymer

ALBIS PLASTIC GmbH

## Message:

ALTECH® PP-H A 2030/156 GF30 CP is a Polypropylene Homopolymer (PP Homopolymer) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America. Typical application: Housings.

Characteristics include:

REACH Compliant

RoHS Compliant

Chemically Coupled

Heat Stabilizer

Homopolymer

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Chemically Coupled		
	Heat Stabilized		
	Homopolymer		
Uses	Housings		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm <sup>3</sup>	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	3.00	cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6400	MPa	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Flexural Modulus	5300	MPa	ISO 178
Flexural Stress	130	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	13	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength	60	kJ/m <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	148	°C	ISO 75-2/A
Vicat Softening Temperature	138	°C	ISO 306/B50
Injection	Nominal Value	Unit	Test Method
Drying Temperature			
Circulation Dryer	80.0 to 120	°C	
Desiccant Dryer	80.0 to 120	°C	

Drying Time		
Circulation Dryer	2.0 to 4.0	hr
Desiccant Dryer	2.0 to 3.0	hr
Processing (Melt) Temp	200 to 270	°C
Mold Temperature	20.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

