

# Plenco 02482 (Transfer)

Phenolic  
Plastics Engineering Co.

Message:

PLENCO 02482 is a general purpose, organic filled phenolic molding compound offering excellent mechanical strength while maintaining dielectric properties at elevated humidity levels. UL recognized under component file E40654. 02482 is available in black.

General Information			
UL YellowCard	E40654-231584		
Filler / Reinforcement	Organic filler		
Features	Good electrical performance		
	Good strength		
	General		
Uses	General		
UL File Number	E40654		
Appearance	Black		
Forms	Particles		
Processing Method	Resin transfer molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm <sup>3</sup>	ASTM D792
Apparent Density	0.65	g/cm <sup>3</sup>	ASTM D1895
Molding Shrinkage - Flow	0.57	%	ASTM D955
Water Absorption (24 hr)	0.29	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (E-Scale)	87		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8550	MPa	ASTM D638
Tensile Strength	58.0	MPa	ASTM D638
Tensile Elongation (Break)	0.80	%	ASTM D638
Flexural Modulus	7950	MPa	ASTM D790
Flexural Strength	94.7	MPa	ASTM D790
Compressive Strength	205	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	19.8	J/m	ASTM D256
Notched Izod Impact	18	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	169	°C	ASTM D648
Continuous Use Temperature	208	°C	ASTM D794
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM E831

Thermal Conductivity (100°C)	0.40	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	9.4E+11	ohms·cm	ASTM D257
Dielectric Strength <sup>1</sup>	11	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	5.10		ASTM D150
Dissipation Factor (1 MHz)	0.053		ASTM D150
Arc Resistance	132	sec	ASTM D495
Comparative Tracking Index (CTI)	175	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Oxygen Index	27	%	ASTM D2863

#### Additional Information

The value listed as Mold Shrink, Linear-Flow, ASTM D955 was tested according to the ASTM D6289 standard. The value listed as Comparative Tracking Index, UL 746 was tested according to ASTM D3638. The value listed as Thermal Conductivity, ASTM C177 was tested according to the ASTM E1461 standard. Post Shrinkage, ASTM D6289, 72hr, 120°C: 0.22% Heat Resistance, ASTM D794: 208°C Drop Ball Impact, PLENCO Method: 98 J/m

Injection	Nominal Value	Unit
Mold Temperature	165 - 182	°C
Back Pressure	0.300	MPa
Screw Speed	< 60	rpm

#### Injection instructions

Transfer Time: 3-8 sec Transfer Pressure: 5.5-6.9 MPa Preheating Temperature: 104-115°C

#### NOTE

- Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT