

Wanthane® WHT-8195RV

Thermoplastic Polyurethane Elastomer (Polyether)

Wanhua Chemical Group Co., Ltd.

Message:

TYPE: Polyether-based grade Extrusion and injection molding grade
FEATURES: Excellent hydrolytic stability, fungus resistance, good low-temperature flexibility, complies with FDA(21 CFR 177.1680, 177.2600), ROHS, ISO 10993 & USP VI
Applications: Electronic parts, wire & cable, medical products, etc

General Information	
Features	Flexibility at low temperatures
	Antibacterial property
	Hydrolysis stability
Uses	Electrical/Electronic Applications
	Wire and cable applications
	Medical/nursing supplies
Agency Ratings	FDA 21 CFR 177.1680
	FDA 21 CFR 177.2600
	ISO 10993
	USP Class VI
RoHS Compliance	RoHS compliance
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	95		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
DIN Abrasion	75.0	mm ³	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	12.0	MPa	ASTM D412
300% strain	25.0	MPa	ASTM D412
Tensile Strength (Break)	38.0	MPa	ASTM D412
Tensile Elongation (Break)	380	%	ASTM D412
Tear Strength	120	kN/m	ASTM D624

Compression Set			ASTM D395
23°C, 24 hr	28	%	ASTM D395
70°C, 22 hr	70	%	ASTM D395
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-40.0	°C	ASTM D3418
Vicat Softening Temperature	105	°C	ASTM D1525
Injection	Nominal Value	Unit	
Drying Temperature	100 - 110	°C	
Drying Time	2.0 - 3.0	hr	
Suggested Max Moisture	0.030	%	
Rear Temperature	200	°C	
Middle Temperature	205	°C	
Front Temperature	210	°C	
Nozzle Temperature	215	°C	
Mold Temperature	23	°C	
Screw L/D Ratio	25.0:1.0 to 30.0:1.0		
Screw Compression Ratio	2.0 : 1.0 - 3.0 : 1.0		
Extrusion	Nominal Value	Unit	
Drying Temperature	100 - 110	°C	
Drying Time	2.0 - 3.0	hr	
Suggested Max Moisture	0.030	%	
Cylinder Zone 1 Temp.	200	°C	
Cylinder Zone 2 Temp.	205	°C	
Cylinder Zone 3 Temp.	210	°C	
Cylinder Zone 4 Temp.	215	°C	
Adapter Temperature	220	°C	
Die Temperature	215	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

