

DuPure® G 72

Polypropylene Homopolymer

Ducor Petrochemicals BV

Message:

Description

DuPure G 72 is a polypropylene homopolymer for extrusion- & thermoforming applications, requiring high transparency and improved stiffness. The product is nucleated and clarified, and contains anti-electrostatic agents. DuPure G 72 TF exhibits excellent processability, and very good optical and mechanical properties of thermoformed parts.

Applications

DuPure G 72 is suitable for: thermoformed packaging, e.g. high transparent trays, cups and containers.

General Information	
Additive	Antistatic
	Clarifier
	Nucleating Agent
Features	Antistatic
	Food Contact Acceptable
	Good Processability
	High Clarity
	Homopolymer
	Nucleated
	Opticals
Uses	Containers
	Cups
	Packaging
Agency Ratings	EC 1907/2006 (REACH)
	EC 1935/2004
	EN 71-3
	EU 10/2011
	EU 2000/53/EC
	EU 2002/96/EC (WEEE)
	EU 2005/84/EC
	EU 94/62/EC
	FDA 21 CFR 177.1520(a) 1 (i)
	FDA 21 CFR 177.1520(c) 1.1a
RoHS Compliance	RoHS Compliant
Appearance	Clear/Transparent
Processing Method	Extrusion

Thermoforming

Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.1	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	90.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2050	MPa	ISO 527-2/1
Tensile Stress (Yield)	41.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	6.0	%	
Break	> 25	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	180	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	5.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	115	°C	ISO 75-2/B
1.8 MPa, Unannealed	69.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	158	°C	ISO 306/A
--	100	°C	ISO 306/B
Melting Temperature (DSC)	165	°C	ISO 3146
Optical	Nominal Value	Unit	Test Method
Haze (1000 µm)	30	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT