

Innothane® IE-8000

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

Message:

IE-8000 is a tough, abrasion resistant elastomer formulated for room temperature hand-batch processing. The unique chemistry of the system imparts excellent electrical properties, hydrolytic stability, and flexibility at low temperatures. Excellent physical properties can be obtained without the utilization of mercury, MOCA, or TDI.

General Information			
Features	Good Abrasion Resistance		
	Good Electrical Properties		
	Good Toughness		
	Hydrolytically Stable		
	Low Temperature Flexibility		
RoHS Compliance	RoHS Compliant		
Appearance	Cream		
Processing Method	Encapsulating		
Physical	Nominal Value	Unit	
Specific Gravity			
Hardener	0.930	g/cm³	
Cured	0.940	g/cm³	
Base Resin	1.20	g/cm³	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.8E+16	ohms	ASTM D270
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 100		
Hardener	Mix Ratio by Weight: 100		
	Mix Ratio by Weight: 35		
Resin	Mix Ratio by Volume: 27		
Demold Time	360 to 480	min	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity			
25°C ¹	0.045	Pa·s	
25°C ²	2.0	Pa·s	

25°C ³	7.0	Pa·s	
Curing Time ⁴	40	hr	
Gel Time	16 to 20	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	75 to 85		ASTM D2240
Tensile Strength	8.07	MPa	ASTM D638
Tensile Elongation at Break	270	%	ASTM D638
Tear Strength	40.3	kN/m	ASTM D624
Electric Strength (25°C)	22	kV/mm	ASTM D149
Relative Permittivity (25°C)	2.40		ASTM D150
Volume Resistivity	2.0E+16	ohms·cm	ASTM D270
Dissipation Factor (1 kHz, 25°C)	0.014		ASTM D150
NOTE			
1.	Resin		
2.	Mixed		
3.	Hardener		
4.	24 hours at 77°F + 16 hours at 160°F		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT