THERMOLAST® K TF9AAB (Series: FC/HE/tl)

Thermoplastic Elastomer

KRAIBURG TPE

Message:

The FC/HE/tl Series is your material solution for applications with food contact, providing excellent resilience properties. The series is available in translucent colors.

Typical applications

Closures

Flexible Connections

Household articles

Membranes

Packaging (for food and careproducts)

Seals

Valves

Material advantages

Applications with food contact

Code of Federal Regulations, Title 21 (CFR 21) "FDA"

Easy coloring (compounds in natural colors)

EN71/3

Excellent mechanical properties

Halogen-free

High resilience

Perfect adhesion to PP

Regulation (EU) No. 10/2011

| General Information | |
|---------------------|--------------------------------------|
| Features | Food Contact Acceptable |
| | Good Adhesion |
| | Halogen Free |
| | Resilient |
| | |
| Uses | Closures |
| | Connectors |
| | Food Packaging |
| | Household Goods |
| | Membranes |
| | Non-specific Food Applications |
| | Packaging |
| | Seals |
| | Valves/Valve Parts |
| | |
| Agency Ratings | EN 71-3 |
| | EU 10/2011 |
| | FDA Food Contact, Unspecified Rating |
| | |
| Appearance | Translucent |

Processing Method

Extrusion

Injection Molding

| Physical | Nominal Value | Unit | Test Method |
|---|---------------------------|-------|-------------|
| Density | 0.900 | g/cm³ | ISO 1183 |
| Hardness | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore A) | 95 | | ISO 7619 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress ¹ (Yield) | 22.0 | MPa | ISO 37 |
| Tensile Elongation ² (Break) | 650 | % | ISO 37 |
| Tear Strength ³ | 66 | kN/m | ISO 34-1 |
| Extrusion | Nominal Value | Unit | |
| Drying Temperature | 60.0 to 80.0 | °C | |
| Drying Time | 2.0 to 4.0 | hr | |
| Cylinder Zone 1 Temp. | 160 | °C | |
| Cylinder Zone 2 Temp. | 180 | °C | |
| Cylinder Zone 3 Temp. | 200 | °C | |
| Die Temperature | 200 to 230 | °C | |
| NOTE | | | |
| 1. | Type S2, 200 mm/min | | |
| 2. | Type S2, 200 mm/min | | |
| 3. | Method Bb, Angle (Nicked) | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

