

# Stat-Tech™ PP-16CP/000 2 HI BLACK

Polypropylene

PolyOne Corporation

## Message:

Stat-Tech™ electrically conductive compounds are specifically engineered to provide anti-static, ESD and RFI/EMI shielding performance for critical electronic applications. These compounds combine the performance of select engineering resins with reinforcing additives such as carbon powder, carbon fiber, nickel-coated carbon fiber and stainless steel fiber for low to high levels of conductivity depending upon application requirements.

General Information			
Filler / Reinforcement	Carbon Powder, 16% Filler by Weight		
Features	Antistatic		
	Conductive		
	Electrically Conductive		
	Statically Conductive		
Uses	Aerospace Applications		
	Automotive Electronics		
	Business Equipment		
	Computer Components		
	Connectors		
	Electrical Housing		
	Electrical/Electronic Applications		
	Housings		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.80 to 1.0	%	
Across Flow	0.80 to 1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	25.5	MPa	ASTM D638
Tensile Elongation <sup>1</sup> (Break)	12	%	ASTM D638
Flexural Modulus	1690	MPa	ASTM D790
Flexural Strength	42.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	320	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method


Deflection Temperature Under Load			ASTM D648
0.45 MPa, Annealed, 3.18 mm	98.0	°C	
1.8 MPa, Annealed, 3.18 mm	50.0	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3 to 1.0E+5	ohms	ASTM D257
Volume Resistivity	1.0E+3 to 1.0E+5	ohms·cm	ASTM D257
Static Decay - (Mil-B-81705C), 12% RH, 5000 kV to 50 kV	2	msec	
Injection	Nominal Value	Unit	
Processing (Melt) Temp	199 to 221	°C	
NOTE			
1.	Type I, 5.1 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
 Phone: +86 13424755533  
 Email: sales@su-jiao.com  
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT