

Hetron™ FR 1540

Vinyl Ester

Ashland Performance Materials

Message:

Ashland Resins for the Pultrusion Market

Chemistry

Fire retardant resin

Performance Attributes

Excellent UV resistance. Good color and chemistry.

Typical Applications

Architectural panels.

General Information		
Features	Flame Retardant	
	Good UV Resistance	
Processing Method	Pultrusion	
Physical	Nominal Value	Unit
Solution Viscosity	6000	mPa · s
Mechanical	Nominal Value	Unit
Tensile Modulus	4340	MPa
Tensile Strength	40.7	MPa
Tensile Elongation (Break)	1.0	%
Flexural Modulus	4340	MPa
Flexural Strength	82.7	MPa
Thermal	Nominal Value	Unit
Heat Deflection Temperature	83	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

