

# mPact™ D143

Metallocene Linear Low Density Polyethylene  
Chevron Phillips Chemical Company LLC

## Message:

This mLLDPE is tailored for applications that require:  
Excellent clarity  
Excellent gloss  
Excellent toughness  
Excellent heat seal  
Typical blown film applications include:  
Seal layer in coextrusions  
Heavy duty packaging  
Clarity packaging

General Information	
Additive	Processing aid
Features	Highlight
	Good heat sealability
	Good flexibility
	Definition, high
	Good toughness
Uses	Blown Film
	Packaging
Forms	Particle
Processing Method	Blow film
	Co-extrusion molding

Physical	Nominal Value	Unit	Test Method
Density	0.916	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.4	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (Blown Film)	> 1.0		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	
secant modulus			ASTM D882
1% secant, MD: 25 µm, blown film	152	MPa	ASTM D882
1% secant, TD: 25 µm, blown film	157	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 25 µm, blown film	11.7	MPa	ASTM D882
TD: Yield, 25 µm, blown film	10.0	MPa	ASTM D882

MD: Broken, 25 µm, blown film	69.6	MPa	ASTM D882
TD: Broken, 25 µm, blown film	52.4	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 25 µm, blown film	520	%	ASTM D882
TD: Broken, 25 µm, blown film	600	%	ASTM D882
Dart Drop Impact (25 µm, Blown Film)	> 800	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 25 µm, blown film	240	g	ASTM D1922
TD: 25 µm, blown film	420	g	ASTM D1922
Seal Initiation Temperature <sup>1</sup> (25 µm, Blown Film)	100	°C	ASTM F88
Optical	Nominal Value	Unit	Test Method
Gloss (60°, 25.4 µm, Blown Film)	130		ASTM D2457
Haze (25.4 µm, Blown Film)	4.0	%	ASTM D1003
Additional Information			
Blown Film produced on LLDPE line, 2.5:1 BUR, 80 mil Die Gap, 8 in Die, 250 lbs/hr, 400°F Melt Temperature.			
NOTE			

1.

Temperature at which 0.3 lb/in  
heat seal strength is achieved. 0.5 s  
dwell, 30 psi pressure, 11.8 in/min  
separation rate.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

