SQUARE® LIM1500-60A/B

Silicone Rubber, LSR

Shenzhen SQUARE Silicone Co., Ltd.

Message:

Liquid silicone rubber material for indoor medium and high voltage resistance terminal Product Description 2-part liquid silicone rubber, which is suitable for injection or extrusion molding with tracking resistance 1A 3.5 grade, mixing ration of parts A:B=1:1, with standing middle and high voltage, catalyzed by platinum .The appearance of A is transparent and B is grey. Key Features Injection molding High tear strength High tear strength A tigh elongation Excellent electric performance A t the temperature of 20 and in the condition of air-proof, the shelf life is 5 days after mixing A and B, the shelf life will decrease with the increasing of the temperature. Applications

| General Information | | | |
|------------------------------|------------------------------------|-------|-------------|
| Features | Fast curing | | |
| | Good electrical performance | | |
| | Good tear strength | | |
| | Track Resistance | | |
| | Extended tensile rate | | |
| | | | |
| Uses | Cable sheath | | |
| | Electrical/Electronic Applications | | |
| | Wire and cable applications | | |
| | | | |
| Processing Method | Extrusion | | |
| | Liquid Injection Molding (LIM) | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.16 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 60 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Strength | 7.17 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 400 | % | ASTM D412 |
| Tear Strength ¹ | 30.0 | kN/m | ASTM D624 |
| Thermoset | Nominal Value | Unit | |
| Thermoset Components | | | |
| Component a | Mixing ratio by weight: 1.0 | | |

| Component BMixing ratio by weight:Pot Life (20°C)7200Shelf Life52Post Cure Time (200°C)4.0Uncured PropertiesNominal ValueColor | ht: 1.0 |
|--|---------|
| Shelf Life52Post Cure Time (200°C)4.0Uncured PropertiesNominal Value | |
| Post Cure Time (200°C)4.0Uncured PropertiesNominal Value | min |
| Uncured Properties Nominal Value | wk |
| | hr |
| Color | Unit |
| | |
| ² Clear/Transparent | |
| ³ Grey | |
| Solids Content 100 | % |
| Viscosity 1100 | Pa·s |
| Curing Time (140°C) 0.17 | hr |
| NOTE | |
| 1. B mould | |
| 2. Part A | |
| 3. Part B | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

