

Ferro PP LPP26BC63UL-BK

Polypropylene

Ferro Corporation

Message:

Ferro PP LPP26BC63UL-BK is a Polypropylene material filled with 26% calcium carbonate. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

General Information			
Filler / Reinforcement	Calcium Carbonate,26% Filler by Weight		
Appearance	Black		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	27.6	MPa	ASTM D638
Flexural Modulus			ASTM D790
Secant	2140	MPa	
Tangent	2340	MPa	
Flexural Strength (23°C)	46.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Gardner Impact	2.26	J	ASTM D5420

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

