

TARODUR 130

Acrylonitrile Butadiene Styrene

Taro Plast S.p.A.

Message:

ABS medium impact resistance, good flow, specially developed for medium/big parts also at low thickness.
Available: all colors, UV stabilized (L), heat stabilized (H), antistatic (AS).

General Information			
Additive	Antistatic		
	Heat Stabilizer		
	UV Stabilizer		
Features	Antistatic		
	Good Flow		
	Good UV Resistance		
	Heat Stabilized		
	Medium Impact Resistance		
Uses	Industrial Parts		
	Thin-walled Parts		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	15	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955
Flow	0.60 to 0.70	%	
Across Flow	0.60 to 0.70	%	
Water Absorption (23°C, 24 hr)	0.15	%	ASTM D570, ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	109		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ASTM D638, ISO 527-2
Tensile Strength (Yield)	45.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	30	%	ASTM D638, ISO 527-2
Flexural Modulus	2300	MPa	ASTM D790, ISO 178
Flexural Stress			
-- ¹	60.0	MPa	ISO 178

Yield	60.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ² (23°C)	15	kJ/m ²	ASTM D256, ISO 179
Notched Izod Impact (23°C, 3.20 mm)	150	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	85.0	°C	ASTM D648, ISO 75-2/A
Continuous Use Temperature ³	60.0	°C	IEC 60216
Vicat Softening Temperature			
--	102	°C	ASTM D1525, ISO 306/A50 5 ⁴
--	93.0	°C	ASTM D1525, ISO 306/B50 6 ⁵
Ball Pressure Test (75°C)	Pass		VDE 0470
CLTE - Flow (-30 to 30°C)	9.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Glow Wire Ignition Temperature (2.00 mm)	550	°C	IEC 60695-2-13
Oxygen Index	< 21	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature			
--	70.0 to 80.0	°C	
Pre-heater	70.0 to 80.0	°C	
Drying Time			
--	1.0	hr	
Pre-heater	3.0	hr	
Processing (Melt) Temp	210 to 240	°C	
Mold Temperature	50.0 to 80.0	°C	
Injection Rate	Fast		
NOTE			
1.	Yield		
2.	6x4x50 mm		
3.	20000 hrs		
4.	Rate A (50°C/h), Loading 1 (10 N)		
5.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

