

UBE Polyethylene J1019

Polyethylene

UBE America, Inc.

Message:

UBE Polyethylene J1019 is a Polyethylene material. It is available in North America for injection molding. Primary attribute of UBE Polyethylene J1019: Good Processability.

General Information			
Features	Good Moldability		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.917	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)	10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	47		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	12.0	MPa	ASTM D638
Tensile Elongation (Break)	450	%	ASTM D638
Apparent Bending Modulus	130	MPa	ASTM D747
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-60.0	°C	ASTM D746
Vicat Softening Temperature	87.0	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

