

# Niche PA66GF50BK

Polyamide 66

Niche Polymer, LLC

## Message:

Niche PA66GF50BK is a Polyamide 66 (Nylon 66) material filled with 50% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage - Flow	7.0E-3	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	235	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	14500	MPa	ASTM D790
Flexural Strength	390	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C, 3.18 mm)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	250	°C	ASTM D648
Melting Temperature	254 to 266	°C	ASTM D789

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

