Hifax TRC 779P HA 9B9 BLACK

Polyolefin

LyondellBasell Industries

Message:

Hifax TRC 779P HA 9B9 BLACK is a talc filled impact modified grade that is typically used for exterior trim applications that has excellent Impact-Stiffness balance and good flowability properties.

| General Information | | | |
|---------------------------------------|----------------------------|----------|-------------|
| Filler / Reinforcement | Talc filler | | |
| Additive | Impact modifier | | |
| Features | Good dimensional stability | | |
| | Impact modification | | |
| | Rigid, good | | |
| | Impact resistance, good | | |
| | Sprayable | | |
| | Good formability | | |
| | Good liquidity | | |
| | | | |
| Uses | Car exterior decoration | | |
| | Outdoor application | | |
| Annogrance | Black | | |
| Appearance | | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density (23°C) | 1.04 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 25 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress (Yield, 23°C) | 18.0 | MPa | ISO 527-2 |
| Flexural Modulus (23°C) | 1700 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength (23°C) | 30 | kJ/m² | ISO 179 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

