

MEGOLON™ HF 8142 NATURAL UV

Thermoplastic

AlphaGary

Message:

A FLEXIBLE, THERMOPLASTIC, ZERO HALOGEN, 105°C RATED, FLAME RETARDED, OLEFINIC, UV RESISTANT COMPOUND INTENDED FOR DEMANDING TELECOMMUNICATION CABLES.

General Information			
Features	Good UV resistance		
	Good flexibility		
	Halogen-free		
	Flame retardancy		
Uses	Communication Cable Jacketing		
Appearance	Natural color		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.47 - 1.53	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/10.0 kg)	2.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw D	57 - 63		ASTM D2240
Shaw D, 15 seconds	48 - 54		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (0.762 mm)	11.7	MPa	ASTM D412
Tensile Elongation (Break, 0.762 mm)	130	%	ASTM D412
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ¹ (136°C, 168 hr)	-6.0	%	UL Unspecified
Change in Ultimate Elongation in Air ² (136°C, 168 hr)	-13	%	UL Unspecified
Change in Tensile Strength ³ (70°C, 4 hr, in ASTM #2 Oil)	-29	%	UL Unspecified
Change in Ultimate Elongation ⁴ (70°C, 4 hr, in ASTM #2 Oil)	22	%	UL Unspecified
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-20.0	°C	ASTM D746
Hot pressing test-% Loss(80°C)	20	%	IEC 811-3-1
Temperature index	> 355	°C	NES 715
Halogen Content			

--	0	%	MIL C-24643
--		mg/g	IEC 754-1
Smoke Index	5.35		NES 711
Toxicity	4.60		NES 713
Acid gas emission pH	5.40		IEC 60754-2
Acid gas emission conductivity	0.380	μS/mm	IEC 60754-2
Extruder Screw Compression Ratio	1.5:1.0 to 2.5:1.0		
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
23°C, 1 MHz	3.58		ASTM D150
23°C, 100 MHz	3.49		ASTM D150
23°C, 200 MHz	3.46		ASTM D150
23°C, 350 MHz	3.45		ASTM D150
23°C, 600 MHz	3.41		ASTM D150
23°C, 1.00 GHz	3.38		ASTM D150
Dissipation Factor			ASTM D150
23°C, 1 MHz	0.022		ASTM D150
23°C, 100 MHz	0.014		ASTM D150
23°C, 200 MHz	0.012		ASTM D150
23°C, 350 MHz	0.010		ASTM D150
23°C, 600 MHz	8.5E-3		ASTM D150
23°C, 1.00 GHz	7.9E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Oxygen Index (3.18 mm)	44	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.040	%	
Cylinder Zone 1 Temp.	154	°C	
Cylinder Zone 2 Temp.	160	°C	
Cylinder Zone 3 Temp.	166	°C	
Cylinder Zone 4 Temp.	171	°C	
Cylinder Zone 5 Temp.	171	°C	
Adapter Temperature	177	°C	
Melt Temperature	171 - 182	°C	
Die Temperature	177	°C	
Extrusion instructions			
Barrier ScrewScreen Pack: 20/20 or 20/40			
NOTE			
1.	Thickness: 30 mil		
2.	Thickness: 30 mil		
3.	Thickness: 30 mil		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

