

Shuman ABS/PC FR380

Polycarbonate + ABS

Shuman Plastics, Inc.

Message:

FR380 GREY (FORMERLY FR705)
OFFERS THIS COMBINATION OF PROPERTIES:
EXCELLENT FLAME RETARDANCY, GOOD IMPACT STRENGTH, EASY PROCESSABILITY, GOOD SURFACE GLOSS, GOOD CHEMICAL RESISTANCE, SELF EXTINGUISHING

General Information			
Features	Flame Retardant		
	Good Chemical Resistance		
	Good Impact Resistance		
	Good Processability		
	Medium Gloss		
	Self Extinguishing		
Appearance	Grey		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR)	4.0 to 10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	41.4 to 55.2	MPa	ASTM D638
Flexural Modulus	2210 to 2620	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	400 to 560	J/m	ASTM D256
Flammability	Nominal Value		Test Method
Flame Rating (3.18 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	79.4 to 110	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	238 to 277	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	79.4 to 110	°C	
Drying Time	3.0 to 4.0	hr	
Melt Temperature	238 to 277	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

