

ARNYL PA66 30% FV INDUSTRIALE NERO

Polyamide 66

Daloga srl

Message:

ARNYL PA66 30% FV INDUSTRIALE NERO is a Polyamide 66 (Nylon 66) material. It is available in Europe.
Typical application of ARNYL PA66 30% FV INDUSTRIALE NERO: Industrial Applications

General Information			
Uses	Industrial Applications		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Ash Content - 1 hrs (750°C)	28 to 32	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8500	MPa	ASTM D638
Tensile Strength (Break)	145	MPa	ASTM D638
Tensile Elongation (Break)	2.4	%	ASTM D638
Flexural Modulus	7500	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	75	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	260	°C	
1.8 MPa, Unannealed	255	°C	
Vicat Softening Temperature			
--	260	°C	ASTM D1525 ¹
--	255	°C	ASTM D1525 ²
NOTE			
1.	Loading 1 (10 N)		
2.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT