

Elastron® G G500.A80.N.ABS

Styrene Ethylene Butylene Styrene Block Copolymer

Elastron USA, Inc.

Message:

A soft, colorable SEBS based thermoplastic elastomer (TPE) compound specially designed for excellent adhesion to ABS/PC.

Bondable to: ABS, PC

General Information			
Features	Block Copolymer		
	Bondability		
	Good Adhesion		
	Good Colorability		
	Soft		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	80		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	3.30	MPa	
300% Strain	7.00	MPa	
Tensile Strength (Break)	18.0	MPa	ASTM D412
Tensile Elongation (Break)	700	%	ASTM D412
Tear Strength	55.0	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 22 hr	25	%	
70°C, 22 hr	67	%	
100°C, 22 hr	86	%	
Additional Information	Nominal Value		Test Method
Ozone Resistance - Stressed	No Cracks		ASTM D518
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Suggested Max Regrind	20	%	
Rear Temperature	170 to 190	°C	

Middle Temperature	180 to 200	°C
Front Temperature	190 to 200	°C
Nozzle Temperature	200 to 210	°C
Mold Temperature	40.0 to 60.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

