ESPOLEX WT515

Thermoplastic Polyolefin Elastomer Sumitomo Chemical America, Inc.

Message:

ESPOLEX WT515 is a polyolefin thermoplastic elastomer (TPO (POE)) product. It can be processed by injection molding and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: automotive industry.

General Information			
Uses	Application in Automobile Field Car interior equipment		
Processing Method	Injection molding		
Physical Physical	Nominal Value	Unit	Test Method
Density	0.880	g/cm³	ASTM D1505
•		g/cm	A31W D1303
Melt Mass-Flow Rate (MFR) (230°C/2 kg)	7.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	340	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	11.0	MPa	ASTM D412
Tensile Elongation ² (Break)	560	%	ASTM D412
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-45°C	No Break		ASTM D256
-40°C	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -60.0	°C	ASTM D746
Injection	Nominal Value	Unit	
Processing (Melt) Temp	199 - 243	°C	
Mold Temperature	21.1 - 48.9	°C	
Injection Rate	Fast		
Back Pressure	0.345 - 0.689	MPa	
Injection instructions			
Injection Pressure: HighPack/Hold Pr	essure: 40-70% of Inj PressScrew RPN	1: SlowPart Draft: 3-6° per sideTool S	Surface Finish: Light Texture
NOTE			
1.	C mold, 500 mm/min		
2.	Mouth die C, 500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

