

Clariant Nylon 6 6001-L

Polyamide 6

Clariant Corporation

Message:

Clariant Nylon 6 6001-L is a Polyamide 6 (Nylon 6) material. It is available in North America. Primary attribute of Clariant Nylon 6 6001-L: Impact Modified.

General Information			
UL YellowCard	E103015-218178		
Additive	Impact Modifier		
Features	Impact Modified		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	68.9	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Flexural Strength	89.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	179	°C	
1.8 MPa, Unannealed	61.7	°C	
Melting Temperature	218	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT