

Petrothene® M2512U

Low Density Polyethylene

LyondellBasell Industries

Message:

PETROTHENE M 2512 is a film grade resin that exhibits good optics, good impact strength and good tensile properties and stiffness. This resin is typically used for general-purpose packaging. M 2512U contains medium levels of antiblock.

General Information			
Additive	Medium Antiblock		
Features	Food Contact Acceptable		
	Good Impact Resistance		
	Good Stiffness		
	Medium Antiblocking		
	Opticals		
Uses	Film		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.925	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.2	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	ASTM D882
Secant Modulus			
1% Secant, MD : 25 µm	221	MPa	
1% Secant, TD : 25 µm	262	MPa	ASTM D882
Tensile Strength			
MD : Break, 25 µm	23.1	MPa	
TD : Break, 25 µm	19.3	MPa	ASTM D882
Tensile Elongation			
MD : Break, 25 µm	330	%	
TD : Break, 25 µm	500	%	ASTM D1709
Dart Drop Impact (25 µm)	85	g	
Optical	Nominal Value	Unit	Test Method
Gloss (60°, 25.4 µm)	100		ASTM D2457
Haze (25.4 µm)	7.5	%	ASTM D1003
Extrusion	Nominal Value	Unit	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

