# RTP 2100 HF

#### Polyether Imide

**RTP** Company

#### Message:

Warning: The status of this material is 'Commercial: Limited Issue' The data for this material has not been recently verified. Please contact RTP Company for current information prior to specifying this grade.

General Information			
Features	High Flow		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm,			
Injection Molded)	0.60 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	3100	МРа	ASTM D638
Tensile Strength	90.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection			
Molded)	10	%	ASTM D638
Flexural Modulus (Injection Molded)	2760	МРа	ASTM D790
Flexural Strength (Injection Molded)	165	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm, Injection			
Molded)	21	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	430	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, Injection Molded)	196	°C	ASTM D648
Injection	Nominal Value	Unit	
Rear Temperature	349 to 382	°C	
Middle Temperature	349 to 382	°C	
Front Temperature	349 to 382	°C	
Mold Temperature	135 to 177	°C	
Injection Pressure	83.0 to 124	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

