

Reslen PPH 15GF

Polypropylene Homopolymer

Polimarky Spolka Jawna

Message:

Reslen PPH 15GF is a Polypropylene Homopolymer (PP Homopolymer) product. It is available in Europe. Primary characteristic: homopolymer.

General Information			
Features	Homopolymer		
Physical	Nominal Value	Unit	Test Method
Density	0.990 to 1.01	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3200 to 3600	MPa	ISO 527-2
Tensile Stress	57.0 to 65.0	MPa	ISO 527-2
Tensile Strain (Break)	2.5 to 5.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.0 to 11	kJ/m ²	ISO 179/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	115	°C	ISO 75-2/A
Vicat Softening Temperature	138	°C	ISO 306/A120
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 120	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	210 to 235	°C	
Mold Temperature	40.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT