

# Sylvin 8600-75C Clear

Polyvinyl Chloride  
Sylvin Technologies Incorporated

Message:  
Sylvin 8600-75C Clear Is A VinylCompound Formulated For Profile Extrusion Applications

General Information	
Features	General
Uses	Industrial application
	General
	Profile
Appearance	Clear/transparent
Processing Method	Extrusion
	Profile extrusion molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw C	75		ASTM D2240
Shaw C, 10 seconds	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	19.7	MPa	ASTM D638
Tensile Elongation (Break)	290	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	87.6	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Melting Temperature	177 - 191	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	25	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

