

# PONYL 4003EPG10

Polyamide 66

POLYROCKS CHEMICAL CO., LTD

Message:

PONYL 4003EPG10 is a Polyamide 66 (Nylon 66) product filled with 10% glass fiber. It is available in Asia Pacific. Typical application: Electrical/Electronic Applications.  
Characteristics include:  
Flame Rated  
Eco-Friendly/Green  
Flame Retardant  
Good Dimensional Stability  
Halogen Free

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Environmentally Sound		
	Flame Retardant		
	Good Dimensional Stability		
	Halogen Free		
	High Heat Resistance		
	Low Density		
Uses	Electrical Parts		
	Electrical/Electronic Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (275°C/0.325 kg)	9.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	90.0	MPa	ASTM D638
Tensile Elongation (Break)	11	%	ASTM D638
Flexural Modulus	5000	MPa	ASTM D790
Flexural Strength	135	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	40	J/m	ASTM D256
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
3.00 mm	V-0		
Injection	Nominal Value	Unit	

Drying Temperature	100	°C
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	245 to 270	°C
Mold Temperature	80.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

