# Exact<sup>™</sup> 4150

### Ethylene-based Plastomer Resin

#### ExxonMobil Chemical

#### Message:

EXACT 4150 is an ethylene-based hexene plastomer produced using ExxonMobil Chemical's EXXPOL® Catalyst Technology. EXACT 4150 is designed for multilayer coextruded cast film applications requiring low sealing temperatures, high oxygen transmission, and high toughness. Typical applications include seal layers for lamination films used in meat, poultry, and fresh produce packaging.

General Information			
Additive	heat stabilizer		
Forms	Particle		
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD	55.4	MPa	ASTM D882
1% secant, TD	59.0	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield	4.72	MPa	ASTM D882
TD: Yield	4.23	MPa	ASTM D882
MD: Fracture	78.0	MPa	ASTM D882
TD: Fracture	70.5	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Yield	11	%	ASTM D882
TD: Yield	9.0	%	ASTM D882
MD: Fracture	470	%	ASTM D882
TD: Fracture	660	%	ASTM D882
Dart Drop Impact	540	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD	160	g	ASTM D1922
TD	350	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	75.0	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	93		ASTM D2457
Haze	0.30	%	ASTM D1003
Legal statement			

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

