CET® 265

Styrene Methyl Methacrylate Acrylic Copolymer

Resirene, S.A. de C.V.

Message:

A transparent styrene-acrylic copolymer with sparkling clarity, good toughness and scratch resistance, that is easy to process.

| General Information | | | |
|--|---------------------------------|----------|-------------|
| Features | Copolymer | | |
| | Good Processability | | |
| | Good Stiffness | | |
| | Good Toughness | | |
| | High Clarity | | |
| | Scratch Resistant | | |
| | | | |
| Uses | Appliances | | |
| | Cosmetic Packaging | | |
| | Medical Devices | | |
| | Medical/Healthcare Applications | | |
| | Packaging | | |
| | Toys | | |
| | | | |
| Appearance | Clear/Transparent | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.03 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (200°C/5.0 kg) | 10 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus ¹ | 1200 | MPa | ASTM D638 |
| Tensile Strength ² (Break) | 19.0 | MPa | ASTM D638 |
| Tensile Elongation ³ (Break) | 150 | % | ASTM D638 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (3.18 mm) | 530 | J/m | ASTM D256 |
| Unnotched Izod Impact (3.18 mm) | No Break | | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 60.0 | °C | ASTM D648 |
| Vicat Softening Temperature | 70.0 | °C | ASTM D1525 |
| Optical | Nominal Value | Unit | Test Method |
| Haze | 4.0 | % | ASTM D1003 |
| Injection | Nominal Value | Unit | |

| Rear Temperature | 160 to 170 | °C | |
|------------------------|------------|----|--|
| Middle Temperature | 170 to 180 | °C | |
| Front Temperature | 180 to 190 | °C | |
| Nozzle Temperature | 200 to 210 | °C | |
| Processing (Melt) Temp | < 250 | °C | |
| Mold Temperature | 40.0 | °C | |
| NOTE | | | |
| 1. | 5.0 mm/min | | |
| 2. | 5.0 mm/min | | |
| 3. | 5.0 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

