

Cri-Line GP-715-LV

Fluoroelastomer

Cri-Tech, Inc.

Message:

66% Fluorine copolymers formulated for injection molding. GP-LV compounds also exhibit the improved hot tear resistance of their higher viscosity counterparts.

General Information		
Features	Copolymer	
	General Purpose	
	Low Viscosity	
Uses	General Purpose	
Processing Method	Injection Molding	
Physical	Nominal Value	Unit
Specific Gravity	1.84	g/cm ³
Fluorine Content	66	%
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	70	
Elastomers	Nominal Value	Unit
Tensile Stress (100% Strain)	3.39	MPa
Tensile Strength	12.3	MPa
Tensile Elongation (Break)	260	%
Compression Set ¹ (200°C, 22 hr)	17	%
NOTE		
1.	Plied discs	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT