

Staramide AG3K

Polyamide 66

Eurostar Engineering Plastics

Message:

Staramide AG3K is a Heat and Hydrolytically Stabilized, 15 % Glass Fiber Reinforced Polyamide 66 Injection Molding Resin

General Information			
UL YellowCard	E340012-100755263		
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Additive	Heat Stabilizer		
	Hydrolysis Resistant		
Features	Heat Stabilized		
	Hydrolytically Stable		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.40 to 0.80	%	Internal Method
Water Absorption (Saturation, 23°C)	7.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6500	MPa	ISO 527-2/1
Tensile Stress (Break)	125	MPa	ISO 527-2/5
Tensile Strain (Break)	3.0	%	ISO 527-2/5
Flexural Modulus ²	6000	MPa	ISO 178
Flexural Stress	175	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength ³ (23°C)	55	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength ⁴ (23°C)	6.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵ (1.8 MPa, Unannealed, 100 mm Span)	230	°C	ISO 75-2/Ae
Vicat Softening Temperature	253	°C	ISO 306/B120
CLTE			ISO 11359-2
Flow : 23 to 60°C	3.5E-5	cm/cm/°C	
Transverse : 23 to 60°C	1.0E-4	cm/cm/°C	
Thermal Conductivity	0.33	W/m/K	ISO 8302
RTI Elec	65.0	°C	UL 746
RTI Imp	65.0	°C	UL 746

RTI Str	65.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ⁶	> 1.0E+16	ohms	IEC 60093
Volume Resistivity	> 1.0E+16	ohms·cm	IEC 60093
Electric Strength (3.20 mm, in Oil)	19	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	3.40		
60 Hz	3.40		
1 MHz	3.20		
Dissipation Factor			IEC 60250
50 Hz	6.8E-3		
60 Hz	6.8E-3		
1 MHz	0.015		
Comparative Tracking Index			IEC 60112
--	550	V	
Solution B	450	V	
Flammability	Nominal Value	Unit	Test Method
Burning Rate			FMVSS 302
2.00 mm	10	mm/min	
3.00 mm	5.0	mm/min	
Flame Rating			UL 94
0.750 mm	HB		
3.00 mm	HB		
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	260 to 280	°C	
Middle Temperature	270 to 280	°C	
Front Temperature	270 to 290	°C	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	60.0 to 90.0	°C	
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4 sp=62mm		
4.	80*10*4		
5.	120*10*4		
6.	ROA		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

