

METLBOND® 1515-4

Epoxy; Epoxide

Cytec Industries Inc.

Message:

Metlbond 1515-4 is a 350°F (177°C) curing modified epoxy supported film adhesives. Metlbond 1515-4 can also be cured at 250°F (121°C). Its maximum continuous service temperature range is 275°F to 320°F (135°C to 160°C).

Metlbond 1515-4 is commonly used for Boeing BMS 5-154 metal-to-metal and composite bonding and BMS 8-341 cosmetic surfacing.

Suggested Applications:

Metal-to-metal bonding

Composite bonding

Cosmetic surfacing

General Information		
Features	Good Surface Finish	
	Heat Cure	
	High Heat Resistance	
	Humidity Resistant	
Uses	Adhesives	
	Aerospace Applications	
	Bonding	
	Metal Bonding	
Appearance	Blue	
Forms	Film	
Thermal	Nominal Value	Unit
Glass Transition Temperature ¹	170	°C
Additional Information	Nominal Value	Unit
Volatiles	< 1.0	%
NOTE		
1.	Dry, G' knee by dynamic mechanical analysis	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT