

POCAN® B 600 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, non-reinforced, injection molding, extrusion, improved flowability

General Information			
Features	Good liquidity		
Agency Ratings	EC 1907/2006 (REACH)		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.31	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	210	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Vertical flow direction: 260°C, 2.00mm ¹	1.6	%	ISO 2577
Vertical flow direction: 150°C, 1 hour, 2.00mm ²	0.30	%	ISO 2577
Flow direction: 260°C, 2.00mm ³	1.6	%	ISO 2577
Flow direction: 150°C, 1 hour, 2.00mm ⁴	0.30	%	ISO 2577

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2700	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	55.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	2.5	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	2.9	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	2800	MPa	ISO 178/A
Flexural Stress			ISO 178/A
3.5% strain, 23°C	85.0	MPa	ISO 178/A
23°C ⁶	100	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	5.6	%	ISO 178/A
ISO Shortname	PBT, G, 05-030		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	40	kJ/m ²	ISO 180/1U

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	74.0	°C	ISO 75-2/A
Vicat Softening Temperature	180	°C	ISO 306/B120

Melting Temperature ⁸	225	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	1.1E-4	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.1E-4	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

