

KumhoSunny PET HEG3630FG

Polyethylene Terephthalate

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HEG3630FG is 30%GF reinforced flame retardant PET resin. HEG3630FG has high rigidity, super shape resistance property, high heat resistance and fatigue resistance. HEG3630FG is mainly used in connector, switch, electric & electron parts etc. requiring flame class, etc.

General Information			
Filler / Reinforcement	Glass Fiber, 30% Filler by Weight		
Features	Fatigue Resistant		
	Flame Retardant		
	High Heat Resistance		
	High Rigidity		
Uses	Connectors		
	Electrical Parts		
	Electrical/Electronic Applications		
	Switches		
UL File Number	E254819		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.68	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	140	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	10000	MPa	ASTM D790
Flexural Strength	210	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	90	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	250	°C	
1.8 MPa, Unannealed	225	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method

Flame Rating (1.60 mm)	V-0	UL 94
Injection	Nominal Value	Unit
Drying Temperature	110 to 130	°C
Drying Time	4.0 to 6.0	hr
Processing (Melt) Temp	230 to 270	°C
Mold Temperature	40.0 to 70.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

