

# Karina BLACK PVC COMPOUND 751-48/1-E-IS-LMP

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

HEAVY METAL FREE PVC COMPOUND RECOMMENDED FOR COAXIAL CABLES JACKETING. ALSO RECOMMENDED FOR PLUG INJECTION.

| General Information                     |                                 |                   |               |
|-----------------------------------------|---------------------------------|-------------------|---------------|
| Uses                                    | Cable Jacketing                 |                   |               |
|                                         | Reflectors                      |                   |               |
|                                         | Wire & Cable Applications       |                   |               |
| Appearance                              | Black                           |                   |               |
| Processing Method                       | Injection Molding               |                   |               |
| Physical                                | Nominal Value                   | Unit              | Test Method   |
| Density <sup>1</sup>                    | 1.37 to 1.43                    | g/cm <sup>3</sup> | IEC 60811-1-3 |
| Color                                   | OK                              |                   | ME 12         |
| Color a                                 | -0.880 to 0.720                 |                   | ME 12         |
| Color b                                 | -1.05 to 0.550                  |                   | ME 12         |
| Color L                                 | 25.9 to 27.5                    |                   | ME 12         |
| Maximum Variation of Elongation         | < 25                            | %                 | IEC 60811-1-2 |
| Maximum Variation of Tensile Strength   | < 25                            | %                 | IEC 60811-1-2 |
| Hardness                                | Nominal Value                   | Unit              | Test Method   |
| Durometer Hardness (Shore A, 15 sec)    | 73 to 77                        |                   | NBR 7456      |
| Mechanical                              | Nominal Value                   | Unit              | Test Method   |
| Tensile Stress                          | > 10.0                          | MPa               | IEC 60811-1-1 |
| Tensile Strain (Yield)                  | > 150                           | %                 | IEC 60811-1-1 |
| Elastomers                              | Nominal Value                   | Unit              | Test Method   |
| Tensile Strength <sup>2</sup>           | > 10.0                          | MPa               | IEC 60811-1-2 |
| Tensile Elongation <sup>3</sup> (Break) | > 150                           | %                 | IEC 60811-1-2 |
| Electrical                              | Nominal Value                   | Unit              | Test Method   |
| Volume Resistivity <sup>4</sup>         | > 3.0E+13                       | ohms · cm         | NBR 5403      |
| NOTE                                    |                                 |                   |               |
| 1.                                      | 24 hr                           |                   |               |
| 2.                                      | Aged in Air for 168 hr at 100°C |                   |               |
| 3.                                      | Aged in Air for 168 hr at 100°C |                   |               |
| 4.                                      | 24 hr                           |                   |               |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHEG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

