

Ultrathene® UE672006

Ethylene Vinyl Acetate Copolymer

LyondellBasell Industries

Message:

Ultrathene UE672 is a series of EVA copolymer resins with good toughness, flexibility and clarity. Typical applications include laminating and heavy duty films as well as injection and blow molding.

General Information	
Features	Copolymer Good flexibility Definition, high Good toughness Compliance of Food Exposure
Uses	Films Laminate
Agency Ratings	FDA 21 CFR 177.1350
Forms	Particle
Processing Method	Film extrusion Blow molding Injection molding

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.50	g/10 min	ASTM D1238
Vinyl Acetate Content	13.5	wt%	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	38	µm	
secant modulus			ASTM D882
1% secant, MD: 38 µm, blown film	90.3	MPa	ASTM D882
1% secant, TD: 38 µm, blown film	91.0	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 38 µm, blown film	6.62	MPa	ASTM D882
TD: Yield, 38 µm, blown film	5.52	MPa	ASTM D882
MD: Broken, 38 µm, blown film	30.5	MPa	ASTM D882
TD: Broken, 38 µm, blown film	29.8	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Yield, 38 µm, blown film	18	%	ASTM D882
TD: Yield, 38 µm, blown film	16	%	ASTM D882
MD: Broken, 38 µm, blown film	300	%	ASTM D882

TD: Broken, 38 µm, blown film	600	%	ASTM D882
Dart Drop Impact (38 µm, Blown Film)	570	g	ASTM D4272
Elmendorf Tear Strength			ASTM D1922
MD: 38 µm, blown film	92	g	ASTM D1922
TD: 38 µm, blown film	130	g	ASTM D1922
Oxygen Transmission Rate (23°C, 38 µm, blown film)	8900	cm ³ /m ² /24 hr	ASTM D3985
Water Vapor Transmission Rate (38°C, 38 µm, blown film)	85	g/m ² /24 hr	ASTM F372
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	80.0	°C	ASTM D1525
Melting Temperature	94.4	°C	DSC
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 38.1 µm, Blown Film)	88		ASTM D2457
Haze (38.1 µm, Blown Film)	1.5	%	ASTM D1003
Additional Information	Nominal Value		Test Method
NAS ¹ (38.1 µm)	78.0		ASTM D1746
Physical properties measured on 1.5 mil film produced on a 2" BGE extruder w/4" Davis-Standard die, 25 mil die gap, 420 °F melt temperature @50 lb/hr, 2:1 BUR.			
Extrusion	Nominal Value	Unit	
Melt Temperature	< 232	°C	
NOTE			
1.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT