LOTTMER HX-064AB

Thermoplastic Elastomer

Lotte Chemical Corporation

Message:

HX-064AB is a fully-crosslinked thermoplastic elastomer(TPE) product.

TPEs can be easily processed with general thermoplastic processing equipments.

It has low compression set, good weatherability and excellent resistance to high temperature, chemicals, and ozone.

Flexible PVC, rubbers (CR, NBR, EPDM etc.) can be replaced with TPE.

| General Information | | | |
|-------------------------------|--------------------------|-------|-------------|
| Features | Good Chemical Resistance | | |
| | Good Processability | | |
| | Good Weather Resistance | | |
| | High Heat Resistance | | |
| | Low Compression Set | | |
| | Ozone Resistant | | |
| | | | |
| Uses | Hose | | |
| RoHS Compliance | RoHS Compliant | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.970 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 70 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress (100% Strain) | 3.43 | MPa | ASTM D412 |
| Tensile Strength (Break) | 7.55 | МРа | ASTM D412 |
| Tensile Elongation (Break) | 530 | % | ASTM D412 |
| Tear Strength | 30.4 | kN/m | ASTM D624 |
| Compression Set (70°C, 72 hr) | 27 | % | ASTM D395 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (-40°C) | No Break | | ASTM D256 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

