

Nypol® PA B3 CNZ0066 NT326

Polyamide 6

Petropol Industry and Trade of Polymers LTDA

Message:

Polyamide 6 in gray color, with good set of thermal properties, electrical and mechanical. Ideal for injection molding.

General Information				
Features		Good Electrical Properties		
Appearance		Grey		
Processing Method		Injection Molding		
Resin ID (ISO 1043)		>PA 6<		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.13 to 1.15	--	g/cm³	ASTM D792
Molding Shrinkage - Flow	1.0 to 1.5	--	%	ASTM D955
Water Absorption (Equilibrium)	1.7	--	%	ASTM D570
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	70.0	60.0	MPa	ASTM D638
Tensile Elongation (Break)	40	110	%	ASTM D638
Flexural Modulus	3000	1500	MPa	ASTM D790
Flexural Strength	100	50.0	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	60	90	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	70.0	--	°C	ASTM D648
Vicat Softening Temperature	205	--	°C	ASTM D1525 ¹
Melting Temperature	215 to 225	--	°C	ASTM D2117
Injection	Dry	Unit		
Drying Temperature	90.0	°C		
Drying Time	4.0	hr		
Processing (Melt) Temp	220 to 240	°C		
Mold Temperature	40.0 to 80.0	°C		
NOTE				

1. Rate A (50°C/h)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

