

Dynacom 104-G15

Polybutylene Terephthalate

Dynachem Co. Ltd.

Message:

Dynacom 104-G15 is a Polybutylene Terephthalate (PBT) material. It is available in Asia Pacific. Primary attribute of Dynacom 104-G15: Flame Rated.

General Information			
UL YellowCard	E164708-224846		
UL File Number	E164708		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54	g/cm ³	ASTM D792
Molding Shrinkage - Flow ¹	0.50 to 1.5	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.070	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²	95.0	MPa	ASTM D638
Tensile Elongation ³ (Break)	4.0	%	ASTM D638
Flexural Modulus ⁴	5880	MPa	ASTM D790
Flexural Strength ⁵	142	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	195	°C	ASTM D648
RTI Elec	120	°C	UL 746
RTI Imp	120	°C	UL 746
RTI Str	120	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.5	ohms · cm	ASTM D257
Dielectric Strength (1.00 mm)	23	kV/mm	ASTM D149
Arc Resistance	50.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.0313 mm)	V-0		UL 94
NOTE			
1.	Thickness: Thickness: 2 to 3 mm		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	3.0 mm/min		
5.	3.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

