

SOFTAPLAS S 75A

Thermoplastic Elastomer

Ovation Polymers Inc.

Message:

Thermoplastic Elastomer - Low tensile set, hydrolytic Stability and excellent balance of properties.

General Information			
Features	Hydrolysis stability		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation ¹ (Break)	500	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256
Additional Information			
Durometer Hardness, ASTM D2240, A Scale (15 sec): 74 - 76Tensile Elongation at Break, ASTM D638, 50 mm/min: >500%			
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT